



ENAMO GRIP

TECHNICAL SHEET

DESCRIPTION

ENAMO GRIP is a two-part aliphatic polyurethane enamel available in clear and colors. It forms a uniquely hard and durable coating film, which demonstrates unsurpassed semi-gloss and color retention, as well as chalk resistance when used in exterior applications. It is resistant to water and humidity, stains, acids, solvents, and chemicals, as well as having tremendous scuff, mar and impact resistance. ENAMO GRIP will self-level to an even and smooth finish.

TYPICAL USES

- For architectural and maintenance solutions that require the utmost in exterior durability
- As a topcoat for RUST GRIP, SUPER THERM and MOIST METAL GRIP
- As a floor covering where a tough, long-lasting finish is required
- Very good alkali resistance and good acid
- Anywhere a solvent-based UV-resistant topcoat is required

APPLICATION METHODS

ENAMO GRIP can be applied to metal, concrete, masonry, wood and other porous surfaces. The application can be by brush, roller, or airless sprayer. For specific instructions on surface preparation, mixing and application, please refer to the SPE's application instructions for ENAMO GRIP.

NOTE: This product must not be applied on or within 2 inches of chlorinated rubber.

NOTE: Never use mineral spirits to prep surfaces or to thin this product.

MINIMUM SPREAD RATE (thickness)

Porous Surfaces – Apply 1 application of RUST GRIP or ENAMO GRIP @ 200 sq ft/gallon (18 m²/gallon); 8 mils wet / 3.92 mils dry (200 microns wet / 98 dry) to absorb into substrate. Apply 2 additional coats of ENAMO GRIP @ 200 sq ft/gallon; 8 mils wet / 3.92 mils dry, each application.

Non-Porous Surfaces – First apply RUST GRIP as a primer; then apply 1 coat of ENAMO GRIP @ 200 sq ft/gallon (18 m²/gallon); 8 mils wet / 3.92 mils dry (200 microns wet / 98 dry), as an architectural coating. Apply a second coat of ENAMO GRIP in areas that might have machine or foot traffic, handrails, or anywhere there is consistent wear on the surface.

Clear Coat Only – Apply 3 applications of ENAMO GRIP @ 200 sq. ft. per gallon (18 m²/gallon) 8 mils wet / 3.0 mils dry (200 microns wet / 78 dry), each application.



TESTS AND CERTIFICATIONS

- USDA Approved
- Marine Approval for Salt Water/Maritime Uses:
 - US Coast Guard (under renewal)
 - ABS (American Bureau of Shipping)
 - IMO (International Marine Organization) (under renewal)
- Flame Spread (ASTM E84) Class A Fire Rating
- Abrasion (ASTM D4060)
- Resistance to Wind-Driven Rain (ASTM D 6904)
- Water Vapor Transmission (ASTM E 96)

PHYSICAL DATA

- Reacted Solids: White - By weight: 64 % / By volume: 49%
- Reacted Solids: Clear - By weight: 44% / By volume: 39%
- 30-60 minutes to tack free at 70°F (21°C)
- Overcoat window is three hours or less at 70°F (21°C)
- Average Perms: 0.6809
- Lead-free / Chromate-free
- Cures by chemical reaction
- Reacted Weight: White: 11.02 lbs/gallon (1,320 kg/lit); Clear: 8.31 lbs/gallon (0,996 kg/lit)
- Aliphatic Polyurethane
- Shelf Life: Up to three years (unopened) under appropriate storage conditions (See SDS)
- Reactive VOC - White: 2.04 lbs/gal (0,244 kg/lit)
- Reactive VOC - Clear: 4.51 lbs/gal (0,540 kg/lit)
- Impact Resistance: (Front) 160 psi / (Back) 100 psi
- Mix Ratio: 3 parts base to 1 part curing agent by volume
- Pot-Life: 4-6 hours at 70°F (21°C), 1 hour at 90°F (32°C). In hot climates (95°F/35°C and above) pot life can reduce to 1.5 hour. Set pails in ice or ice water to extend pot life.
- All colors available with established minimum ordered quantities
- Apply between 40°F (4.4°C) and 100°F (38°C)
- Maximum Surface Temperature when applying: 150°F (65°C)
- Minimum Surface Temperature when applying: 40°F (4.4°C)
- Maximum Surface Temperature after curing: 300°F (149°C)
- In hot (90°F) temperatures and 85% relative humidity (RH), cut the ENAMO GRIP 4-gallon kit with one quart of MAK solvent (Methyl n-Amyl Ketone) to slow down the flash off and skinning of the surface film



SUPERIOR PRODUCTS
EUROPE

ENAMO GRIP

TECHNICAL SHEET

SAFETY PRECAUTIONS

Do not use this product without first taking all appropriate safety measures to prevent property damage and injuries. These measures may include, without limitation: proper ventilation, use of proper lamps, wearing of protective clothing and masks, tenting, and proper separation of application areas. This coating is flammable. Keep away from flame, fire, or other sources of ignition. For more specific safety procedures, please refer to the ENAMO GRIP Material Safety Data Sheet.

KEEP OUT OF REACH OF CHILDREN.

***LIMITATION OF LIABILITY:** All recommendations or suggestions relating to the use of the products, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge is reliable. The products and information are designed for users having the requisite knowledge and industrial skills, and the end-user has the responsibility to determine the suitability of the product for its intended use. SPE has no control over either the quality of condition of the substrate, or the many factors affecting the use and application of the product. Therefore, SPE does not accept any liability arising from loss, injury, or damage resulting from such use or the contents of this data sheet. The information contained in this data sheet is subject to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and the user has the responsibility to ensure that this sheet is current prior to using the product.*

V-11-21-14

Apr-15

Superior Products Europe nv/sa

Kampweg 123 | B-2990 Wuustwezel | Belgium

Phone: +32 3 690 02 40 | Fax: +32 3 690 02 41 | www.specoating.com | info@specoating.com

